

ACERO INOXIDABLE, CARBONO U ALEADOS

Grade	DIN Designation	UNS	SS	AFNOR	AISI	BS
1,4005	X 12 CrS 13	S 41600	2380	Z 12 CF 13	416	416 S21
1,4006	X 10 Cr 13	S 41000	2302	Z 12 C 13	410	410 S21
1,4016	X 6 Cr 17	S 43000	2320	Z 8 C 17	430	430 S 15
1,4021	X 20 Cr 13	S 42000	2303	Z 20 C 13	420	420 S 37
1,4034	X 46 Cr 16		(2304)	Z 40 C 14		/420 S 45)
1,4057	X 12 CrNi 172	S 43100	2321	Z 15 CN 162	431	431 S 29
1,4104	X 12 Cr Mos17	S 43020	2383	Z 10 CF 17	430F	(441 S 29)
1,4112	X 90 CrMoV 18	S 44003				440 B
1,4122	X 35 CrMo 17					
1,4301	X 5 CrNi 18 10	S 30400	2332	Z 6 CN 18,09	304	304 S 15
1,4305	X 10 Cr Nis 18 9	S 30300	2346	Z 10 CNF 18,09	303	303 S 21
1,4306	X 2 CrNi 19 11	S 30403	2352	Z 2 CN 18,09	304L	304 S 12
1,4310	X 12 CrNi 17 7	S 30100	2331	Z 12 CN 17,07	301	
1,4401	X 5 CrNiMo 17 12 2	S 31600	2347	Z 6 CND 17,11	316	316 S 16
1,4404	X 2 CrNiMo 17 13 2	S 31603	2348	Z 2 CND 17,12	316L	316 S 12
1,4435	X 2 CrNiMo 18 14 3	S 31603	2353	Z 2 CND 17,13	316L	316 S 12
1,4436	X 5 CrNiMo 17 13 3	S 31600	2343	Z 6 CND 17,12	316	316 S 16
1,4438	X 2 CrNiMo 18 16 4	S 31703	2367	Z 2 CND 19,15	317L	317 S 12
1,4439	X 2 CrNiMo 17 13 5				317 LNM	
1,4449	X 5 CrNiMo 17 13	S 31700			317	317 S 16
1,4460	X 8 CrNiMo 27 5	S 32900	2324			329
1,4462	X 2 CrNiMo 22 5	S 31803		Z 5 CND 21,08	DUPLEX	
1,4539	X 2 CrNiMoCu 25 20 5	N 08904	2562	Z 1 NCDU 25,20	904L	
1,4541	X 6 CrNiTi 18 10	S 32100	2337	Z 6 CNT 18,10	321	321 S 12
1,4550	X 6 CrNiNb 18 10	S 34700	2338	Z 6 CNNB 18,10	347	347 S 17
1,4571	X 6 CrNiMoTi 17 12 2	S 31635	2350	Z 8 CA 7	316 Ti	320 S 17
1,4713	X 10 CrAl 7					
1,4724	X 10 CrAl 13					
1,4742	X 10 CrAl 18			Z 10 CAS 18		
1,4762	X 10 CrAl 24	(S 44600)	(2322)	Z 10 CAS 24	(446)	
1,4821	X 20 CrNiSi 25 4					
1,4828	X 15 CrNiSi 20 12	(S 30900)		Z 15 CNS 20,12	(309)	(309 S 24)
1,4841	X 15 CrNiSi 25 20	S 31400		Z 15 CNS 25,20	314	
1,4845	X 12 CrNiSi 25 21	S 31008	2361	Z 15 CN 20,12	310S	310 S 24
1,4864	X 12 CrNiSi 36 16	N 08330		(Z 12 CN 37,18)	330	
1,4876	X 10 CrNiAiSi 32 20			Z 8 NC 32,21		3076NA15 H
1,4878	X 12 CrNiTi 18 9	S 32100	2337	Z 6 CNT 18,12	321	321 S 20
2,4068	LC Ni 99.2				B 160	
2,4360	Ni Cu 30 Fe				B 164	3076 NA13
2,4375	Ni Cu 30 Ai					3076NA18
2,4610	Ni Mo 16 Cr 16 Ti					3076NA45
2,4816	Ni Cr 15 Fe				B 166	3076NA14
2,4856	Ni Cr 21 Mo					3076NA43